

Oberursel, 24th October 2017

Chemical resistance of WRAPTEC®

Hereby Monier Roofing Components confirms the resistance or not resistance of the product WrapTec against the substances listed. Substances not listed have to be tested separately.

Chemical	Concentration (%)	Resistance
Acetone (C_3H_6O)	100	resistant
Aluminium chlorid ($AlCl_3$)	saturated	resistant
Benzine	-	not resistant
Bleach liquor ($NaClO$)	10	not resistant
Boric acid (H_3BO_3)	saturated	resistant
Calium chloride ($CaCl_3$)	saturated	resistant
Chlorine	marginal	not resistant
Chlorid acid ($HClO_3$)	20	not resistant
Chlorine water ($HOCl$)	saturated	not resistant
Diesel oil	100	not resistant
Glycerin ($C_3H_8O_3$)	100	resistant
Potassium chloride (KCl)	saturated	resistant
Caustic potash (KOH)	10	resistant
	60	not resistant
Copper sulphate ($CuSO_4$)	saturated	resistant
Table salt ($NaCl$)	saturated	resistant
Methanol (CH_3OH)	100	resistant
Nitrous exhaust fumes (NO_x)	Trace	resistant
	higher	not resistant
Oil (ethereous/ vegetable/ animale)	-	not resistant
Hydrochloric acid (HCl):	10	resistant
	30	not resistant
	conc.	not resistant
Sea water	-	resistant
Sulphuric (H_2SO_4)	10	resistant
	50	not resistant
Tar	-	not resistant
Urine	-	resistant

Axel Rump / Geschäftsführer